



Period Embossed Victorian Tiles

Technical Data & Fixing Instructions

Technical Advice

H&E Smith, Inc.™ supply a wide variety of bespoke tiles for their clients, which can be produced to satisfy individual customer requirements such as colour matching, special sizes and unusual shapes. Please contact us for a quotation.



Period Embossed Victorian Tiles - Product Description

Glazed dry pressed ceramic wall tile 153 x 153 x 9mm, on white biscuit, conforming to EN 14411 BIII with a water absorption >10%, manufactured by a double fired system.

If tiles are to be used outside or in a shower location it is recommended that they are treated with a silicon sealant at the time of manufacture, (this service can be carried out at an extra charge), and failure to do so may result in discolouration. We cannot guarantee against frost damages.

Fixing **NOTICE.**

Apply to a sound, clean surface. Avoid using sand and cement. Any well known brand of adhesive such as Ardex or similar is preferred.

Grouting **WARNING!**

Some coloured grouts can cause unavoidable stains on certain glazed surfaces. Therefore, tests should be made on a spare tile before using any coloured grout, to establish whether it is liable to stain, in which case a surface sealer is necessary to prevent such staining.

Crazing & Shading **CAUTION!**

Victorian tiles are reproduced using similar materials and methods to the original item, and a degree of shade variation is inherent and desirable. We recommend that before fixing it is essential to lay them out in good light, to ensure an acceptable blend of colour and size. Cont...

Glazed tile may craze with time; therefore in this respect no guarantees can be given.

Cleaning **WARNING!**

In certain conditions Victorian glazes with high oxide content can sometimes develop a metallic sheen or stain after contact with certain liquids including prolonged water contact, detergents, acids or alkalis and some cleaning products. Period Embossed Victorian Tile colours should not be used in areas where contact with such substances may occur. Period Embossed Victorian Tiles should be washed using either clean water or pH neutral detergent. Dry off and polish with a cloth.

Property	ISO-Test	Standard EN 14411 Bill	H&E Smith Standard
Length and width	10545-2	+/- 0.5%	+/- 0.4%
Thickness	10545-2	+/- 0.6%	+/- 0.4%
Straightness of sides	10545-2	+/- 0.3%	+/- 0.2%
Warp age	10545-2	+/- 0.5%	+/- 0.4%
Water absorption	10545-3	>10%	19%
Bending strength	10545-4	15 N/mm ²	24 N/mm ²
Coefficient of expansion	10545-8	9 x 10 ⁻⁶ [K-1]	7.5 x 10 ⁻⁶ [K-1]
Thermal shock resistance	10545-9	Required	Resistant
Frost resistance	10545-12	Not required	Not resistant

All measurements are in mm unless stated otherwise.
For samples, specification data or technical advice, please get in touch.

Consumer Notice: (i) the consumer can obtain a new copy of the Fixing Instructions on the [H&E Smith, Inc.™ website](https://www.hesmithtiles.com) in the event that the consumer ever loses his/her copy, or, in the event that H&E Smith, Inc.™ modifies the Fixing Instructions and (ii) H&E Smith retains the right to modify the Fixing Instructions as it deems appropriate and that the consumer is charged with the knowledge of the Fixing Instructions set forth in any modifications.

Disclaimer: It is not possible for H&E Smith to warn the consumer about every possible danger related to use of the product and the consumer must use his or her own common sense and good judgement when using the product.

© H&E Smith, Inc. 2023

These Instructions are the Property of H&E Smith. Reproduction, copies, derivative works, distribution, and public display of these instructions are only permitted with the advance written consent of H&E Smith, Inc.™

Call: [00 44 1782 281617](tel:00441782281617) | Email: info@hesmithtiles.com | Website: www.hesmithtiles.com